

(19) World Intellectual Property Organization  
International Bureau




(43) International Publication Date  
11 January 2001 (11.01.2001)

PCT

(10) International Publication Number  
**WO 01/02614 A1**

- (51) International Patent Classification<sup>7</sup>: **C22C 23/02**, 23/06
- (54) Agent: ANDERSON, Elin; Norsk Hydro ASA, N-0240 Oslo (NO).
- (21) International Application Number: PCT/NO99/00324
- (22) International Filing Date: 25 October 1999 (25.10.1999)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
19993289 2 July 1999 (02.07.1999) NO
- (71) Applicant (for all designated States except US): **NORSK HYDRO ASA** [NO/NO]; N-0240 Oslo (NO).
- (81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **PETTERSEN, Ketil** [NO/NO]; Gråsteinveien 14, N-3931 Porsgrunn (NO). **VIDEM, Marianne** [NO/NO]; Tømmerveien 54, N-3943 Porsgrunn (NO). **SKAR, Jan, Ivar** [NO/NO]; Lærer Johnsens vei 2, N-3960 Stathelle (NO).
- Published:  
— With international search report.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: CORROSION RESISTANT Mg BASED ALLOY CONTAINING Al, Si, Mn AND RE METALS



(57) Abstract: Magnesium alloy with improved corrosion resistance comprising magnesium, 1.5-5 weight % Al, 0.6-1.4 weight % Si, 0.01-0.6 weight % Mn and 0.01-0.4 weight % RE. Method of improving the corrosion resistance of magnesium, aluminium, silicon alloys where Mn is added in order to reduce FE impurities, by keeping both Mn and Fe at a low level by adding small amounts of RE.

200250 "TEH6T00T"



WO 01/02614 A1